

NISOTEC PROCESNO ULJE

NISOTEC PROCESNA ULJA are naphthenic process oils of different grades: N10, N15, N22, N32, N46, N68, N100, N200.

Performance Levels: SRPS ISO 6743-10 (L-Y)

Characteristics

Properties	Units	Typical Values								Methods
		VG 10	VG 15	VG 22	VG 32	VG 46	VG 68	VG 100	VG 200	
Density at 15°C	g/cm ³	0.90	0.90	0.91	0.91	0.92	0.92	0.92	0.92	EN ISO 3675
Kinematic viscosity at 40°C	mm ² /s	10	16	20	36	46	68	100	200	ISO 3104
Flash point COC, min	°C	150	155	160	180	185	185	205	210	EN ISO 2592
Pour point, max	°C	- 39	-30	-25	-20	-20	-20	-9	-6	ISO 3016

Storage and handling instructions

Store in the original container in dry, properly ventilated area. Keep away from direct flame and other sources of ignition. Protect from direct sunlight. Recommended storage temperature: max. 40°C

Packaging

0.1L	0.25L	0.5L	1L	4L	10L	60L	180KG	850KG	IBC	AC
							X			